

Orchid



Balance Nitrile Powder – Free



Its balance of protection and tactile sensitivity convinced users at all different kind of applications. While it can be used as a medical examination and Category III protective glove, this latex-free protection comes in handy, while you work on glass equipment in laboratories or kitchens.

The finger-texturing allows optimal performance by a high a degree of sense of touch throughout the glove film. The finished surface allows grabbing of any smooth and wet surface without losing grip to it, while protecting from any surroundings that should not come in contact with bare skin.



**STGT Gloves are produce with
100% Sustainable biomass energy**

The gloves were tested against 29 chemotherapy drugs according to ASTM D6978, which presently is the most stringent test method for protective gloves against chemical permeation.

No permeation against Fentanyl drugs
No permeation up to 240 minutes when the gloves were tested in accordance to ASTM D6978.



「Touch Of Life」™

COMPLIES TO

ASTM D6319	EN 455	JIS T9115	ISO 11193
Length: Min 220mm (XS-S), Min 230mm (M-XL)	Length: Median ≥ 240mm	Length: Min 230mm	Length: Min 220mm (XS-S), Min 230mm (M-XL)
Single Wall Thickness (Finger): Min 0.05mm	Single Wall Thickness (Finger): -	Single Wall Thickness (Finger): Smooth Min 0.08mm / Textured Min 0.11mm	Single Wall Thickness (Finger): Smooth Min 0.08mm / Textured Min 0.11mm
Elongation: (Before/After Aging): Before 500%/ After 400%	Elongation: (Before/After Aging): -	Elongation: (Before/After Aging): Before Min 500%/ After Min 450%	Elongation: (Before/After Aging): Before 500%/ After 400%
Tensile Strength (Before/After Aging): Before Min 14Mpa/ After Min 14Mpa	Force At Break (Before/After Aging): Before Median ≥ 6N/ After Median ≥ 6N	Tensile Strength (Before/After Aging): Before Min 15Mpa/ After Min 11Mpa	Force At Break (Before/After Aging): Before Min 7N/ After Min 7N

*For other standards please contact us

Used for



"The Jack Of All"

Micro textured finger
precise grip

Single wall thickness (finger)
typical value 5.1 mil (0.13 mm)

Superior strength
comfort & flexibility

Latex protein free

Powder free

Efficient and easy donning

MDD CLASS 1

Superb protection against viral
penetration and chemical permeation

PPE CAT III CE 2777

240 mm length (median)

PPE CAT I CE

Food contact compliance

Average weight 4.8±0.2g for size M

Sustainability Certificates



amfori BSCI
Trade with purpose



ecovadis

Factory Certificates



To Discover our 'Touch Of Life' product line
Please visit www.sritranggloves.com or contact

glove_global@sritranggroup.com

